

BERAM 3060 LM
EXTRA LOW MODULUS
HOT APPLIED JOINT SEALANT

PHYSICAL PROPERTIES
BERAM 3060 EXTRA LOW MODULUS

ASTM 6690 Type 4 (Modified) formerly D-3405 Modified – Extra Low Modulus

PROPERTIES	TEST METHODS	SPECIFICATIONS	TYPICAL RESULTS
Penetration @ 25°C 150 G, 5 sec.	ASTM D-5329	100 - 150	120
Penetration @ -18°C	ASTM D-5329 MODIFIED	25 MIN	32
Flow @ 60°C	ASTM D-5329	10 MM MAX	3
Bond @ -29°C 200% ext – ½"	ASTM D-5329	3 CYCLES	PASS
Resiliency @ 25°C	ASTM D-5329	30 – 60%	54
Asphalt Compatibility	ASTM D-5329	PASS	PASS

McAsphalt Industries Ltd.
8800 Sheppard Avenue East
Toronto, Ontario M1B 5R4
Tel: (416) 281-8181 Fax: (416) 281-8842
Email: info@mcasphalt.com